



Review Article

A Review on Green Synthesis of Sulfur Nanoparticles *via* Plant Extract, Characterization and its Applications

Suresh Ghotekar^{1*}, Trupti Pagar², Shreyas Pansambal³, Rajeshwari Oza³

^{1*} Department of Chemistry, Sanjivani Arts, Commerce and Science College, Kopergaon 423 603, Savitribai Phule Pune University, Maharashtra, India

² Department of Chemistry, G.M.D Arts, B.W Commerce and Science College, Sinnar, 422 103, Savitribai Phule Pune University, Maharashtra, India

³ Department of Chemistry, S.N. Arts, D.J.M. Commerce and B.N.S. Science College, Sangamner 422 605, Savitribai Phule Pune University, Maharashtra, India

ARTICLE INFO

Article history

Submitted: 2020-05-18

Revised: 2020-06-06

Accepted: 2020-06-22

Available online: 2020-06-27

Manuscript ID: [AJCB-2005-1035](#)

DOI: [10.22034/ajcb.2020.109501](#)

KEYWORDS

Applications

Green nanotechnology

Mechanism


Plant extract

Sulfur nanoparticles

ABSTRACT

Among diverse non-metal nanoparticles (NPs), sulfur nanoparticles (SNPs) are one of the most significant and intriguing nanomaterials. An important concern about the synthesis of SNPs is the formation of hazardous wastes, noxious by-products and ruinous pollutants. The best solution to mitigate and/or exclude these noxious substances are plant mediated biosynthesis of SNPs. Eco-benevolent SNPs from plant extracts have been identified as precious nanomaterial in various agricultural, biomedical and catalytic applications including lithium-sulfur batteries, pesticides, fungicides, carbon nanotube modification, gas sensor and neutron capture in cancer therapy because of their splendid performance and selectivity. They have captured the consideration of researchers owing to their sustainable, economical, non-noxious, convenient, green and eco-benevolent nature. This review attempts to cover the recent advancements in the biosynthesis, characterization techniques and applications of biogenic SNPs in environmental and biomedical systems. Furthermore, the stability of biosynthesized SNPs and mechanism of their formation are briefly discussed.

GRAPHICAL ABSTRACT



* Corresponding author: **Suresh Ghotekar**

✉ E-mail: ghotekarsuresh7@gmail.com

☎ Tel number: +918698255427

© 2020 by SPC (Sami Publishing Company)



Introduction

In recent times, scientists have found the gigantic capability behind nanotechnology and since it has played an overriding role in this era. Nanotechnology is definitely receiving in popularity owing to the advantages and prospects it can provide to human being. Therefore, day by day nanomaterials display eclectic and novel biological and physicochemical properties in the domain of nanotechnology. They have miraculous applications of diverse fields; namely, agriculture, pharmaceuticals, catalysis, transportations, bioengineering, water purification, biosensors, textiles, food technology, electronics, optoelectronics, ceramics, health care, information storage, fuel, solar energy, medicine, sensing, and automobiles [1-30].

The non-metal sulfur has numerous uses for pharmaceuticals and agriculture industry [31-32]. Also, sulfur used as a component of fertilizers such as calcium sulphate which is the most common fertilizer in agriculture used to improve the nutritious quality of phosphorous and nitrogen fertilizers [33]. Therefore, SNPs have significant applications (Fig. 1) in several fields of modern technology including, lithium-sulfur batteries [34], pesticides [35], fungicides [36], carbon nanotube modification [37], gas sensor [38], catalysis [39] and neutron capture in cancer therapy [40]. Moreover, SNPs generated significant roles in the arena of biomedical concerns such as antibacterial and pharmacokinetic purpose [41], anticancer activity [42], antitumor and antioxidant activity [43] and wound healing activity [44].

Till date, several approaches were applied into production of SNPs such as microemulsion method [46], surfactant assisted method [47], solvent free method [48], precipitation method [49], electrochemical method [50], egg shell membrane assisted method [51], liquid phase chemical precipitation method [52], heating sulfur powder with polyethylene glycol PEG-600 [53], supersaturated solvent method [54],

ultrasonic method [54], membrane-assisted precipitation method [55] and sodium polysulphide hydrolysis method [56]. However, aforesaid approaches have a high yield capacity, but at the same time they have lacks such as the raise energy cost, requires complicated, tedious, time-consuming and pernicious processes. Therefore, need to enhance of reliable and efficient synthetic approaches to avoid and/or mitigate the limitations through “green nanotechnology”. Indeed, parts of plant extract assisted NPs syntheses have become predominant due to the sustainable, safer, affordable, non-noxious rapid synthesis and simplicity in protocols [5-10]. Also, plant extracts assisted NPs generates an excellent route for SNPs synthesis as they provide herbal reductants and stabilizing agents [2-3]. This review presents current advancements in the eco-benign, sustainable, facile, non-noxious, clean, reliable and green synthesis of SNPs. Besides, the diverse and significant applications of SNPs in agriculture, biomedicine and environmental remediation have been investigated in this review. In addition, the probable reaction mechanisms using bio-reducing/stabilizing compounds in plant broths involved in the green synthesis of SNPs are discussed.




Fig. 1. Diverse applications of SNPs.

Green Synthesis of SNPs

Nowadays, researchers have established it economical to synthesize bio-NPs (**Fig. 2**) from plants, yeasts, algae and fungus as they are reliable, cost-effective, capable, straightforward and readily accessible. In accomplishing this prowess, scientists have explored various approaches to developing efficient nanomaterials. Hence, the green synthesis route utilizing biological specimens has emerged as a facile, affordable and environmentally benevolent. The green methodologies are the preferred route for NPs synthesis because of its viability, non-noxious, ecological friendliness, and well-being to human health and environment when compared with known physical and chemical approaches. In recent times, plant assisted NPs production using plant part extracts and/or living plant has been mentioned in literatures [2-3].

The usage of plant materials in the fabrication of NPs engages the secondary phytochemical/metabolites such as flavonoids, alkaloids, saponins, proteins, phenols, carbohydrates, quinine, glycosides and tannins [5-6]. Biological constituents played a key role as herbal reducers and/or stabilizers in the procedure of forming NPs [7-8]. Although the precise mechanism involved in NPs biosynthesis using extracts from various plants is dubious, it has been noticed that the biomolecules in plant extract such as protein, phenol, flavonoids and vitamins play essential roles in the reduction and capping the biosynthesized NPs [9-10]. The biogenic synthesis of plant assisted SNPs have been carried out by several scientists using typical plants (**Table 1**). Afterwards, the fabricated SNPs need to be explored using known characterization techniques.

Protocol for Green Synthesis of SNPs

Biogenic synthesis of SNPs is an effortless, convenient, efficient, one pot synthesis and eco-accommodating approach without intervention

of any noxious and perilous additives. SNPs are prepared to use typical parts of plants such as pods, leaves, peels, barks and fruits (Table 1). A wholly sustainable and procurable approach is applied for their complete biosynthesis (Fig. 3). In plant extract assisted approaches to SNPs production utilizing fresh and/or dried plant materials such as pods, leaves, peels, barks and fruits are washed with distilled water, cut into fine pieces using kitchen blenders and boiled in double distilled water to acquired plant broth. The plant extract may additionally be purified by certain procedures like centrifugation and/or filtration. Different concentrations of sodium thiosulfate or sodium sulfide and extract of plant at various pH, pressure, temperature and time interval can be used for preparation of SNPs. The extract from plants is completely mixed with the diverse concentrations of sodium thiosulfate or sodium sulfide solution and their conversion into SNPs take place within minutes in safe, efficient, convenient, one pot, rapid, sustainable and eco-benevolent manners. Due to multifarious phytoconstituents are already present in the plant extract and behaves as herbal reducing, capping and/or stabilizing agents, therefore there is no requirement to involve external pernicious stabilizing/capping substances.



Fig. 2. Advantages of green synthesis of NPs.

Table 1. Biosynthesis of SNPs using different plant source with morphology and size

Sr. No	Name of Plants	Part	Precursors	Shape	Size	Ref.
1	<i>Acanthe phylum bracteatum</i>	-	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	-	40 nm	57
2	<i>Alianthus altissima</i>	Leaves	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	-	5-80 nm	58
3	<i>Albizia julibrissin</i>	Fruits	$\text{Na}_2\text{S}_2\text{O}_3$	Spherical	20 nm	59
4	<i>Allium sativum</i>	-	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	Spherical	56.61 nm	60
5	<i>Azadirachta indica</i>	Leaves	Na_2S	Spherical	89 nm	61
6	<i>Catharanthus roseus</i>	Leaves	Na_2S	Spherical	86 nm	61
7	<i>Mangifera indica</i>	Leaves	Na_2S	Spherical	95 nm	61
8	<i>Polyalthia longifolia</i>	Leaves	Na_2S	Spherical	62 nm	61
9	<i>Ficus benghalensis</i>	Leaf	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	Random shape	2-15 nm	62
10	<i>Cinnamomum zeylanicum</i>	Barks	-	-	-	63
11	<i>Melia azedarach</i>	Leaves	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	-	20 ± 4 nm	64
12	<i>Oscimum basilicum</i>	Leaves	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	Spherical	23 nm	65
13	<i>Punica granatum</i>	Peels	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	Spherical	20 nm	66
14	<i>Rosmarinus officinalis</i>	Leaves	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	Spherical	20 nm	67
15	<i>Rosmarinus officinalis</i>	Leaves	$\text{Na}_2\text{S}_2\text{O}_3 \cdot 5\text{H}_2\text{O}$	Spherical	40 nm	68
16	<i>Sophora japonica</i>	Pods	$\text{Na}_2\text{S}_2\text{O}_3$	Spherical	60 nm	69

The brief procedure of biogenic syntheses of SNPs by *Punica granatum* peels extract is described by authors demonstrated in [66]. A fine SNPs powder is obtained and collected for further application as well as characterization purposes.

Plausible mechanism for biogenic synthesis of SNPs

Recently, there have been few published reports on the green synthesis of SNPs using plant extracts. Nevertheless, only a few attempts have been made to investigate the reaction mechanism. Plant extracts are complex mixtures

of active reducing biomolecules such as antioxidant, coumarins, flavonoids, saponins, polyphenols, steroids, and phenolic acids.

Tripathi and co-workers synthesized SNPs by using *Ficus benghalensis* leaves extract. He demonstrated to his studies that the proteins and phytochemicals present in the leaves extract behaves as reducing/stabilizing agents who led to the formation of stable SNPs via disproportionation reaction.

When these proteins/phytochemicals and citric acids are mixed with thiosulfate solutions, instantaneous reduction of S^{6+} to S^0 by proteins/phytochemicals and oxidation of S^{2-} to S^0 by citric acid occur simultaneously through the disproportionation process. Then S^0 undergoes a nucleation process to reach its optimum size and

shape that is influenced by various parameters such as the nature of reducing and/or capping agents, pH and temperature. He beautifully depicted the probable mechanism of formation of SNPs (Fig. 3).

Awwad and co-workers synthesized SNPs using pods extract of *Sophora japonica*. He reported on his studies that sodium thiosulfate solutions mixed with pods extract of *Sophora japonica*. Further, addition of hydrochloric acid into the solution, which releases sulfur ion in the solution, which dispersed and capped by pods extract from *Sophora japonica*. The plausible reaction and mechanism is described in Fig. 4.




Fig. 3. Possible mechanism of green synthesis of SNPs by using *Ficus benghalensis* leaves extract [Reproduced from ref. 62].




Fig. 4. Mechanism for the green synthesis of SNPs by using *Sophora japonica* pods extracts [Reproduced from ref. 69].

Moreover, Khairan and co-workers described green synthesis of SNPs using *Allium sativum*. He reported to his studies that the sulfur ions bind to the garlic metabolites and stabilizing agents and then reduce to sulfur atoms into complex forms of metabolites and sulfur atoms, which form SNPs through a nucleation process. This process continued until the SNPs assumed a stable shape and size. The plausible mechanisms of SNPs formation are depicted in Fig. 5.

Characterization Techniques for SNPs

NPs are mostly characterized by their topography, size, dispersity and surface area. The

known techniques are analyzing NPs characteristics. These approaches involve a range of several techniques like, UV- vis spectroscopy, X-ray diffraction (XRD), fourier transform infrared spectroscopy (FT-IR), scanning electron microscopy (SEM), transmission electron microscopy (TEM), energy dispersive spectroscopy (EDS), atomic force microscopy (AFM) and dynamic light scattering (DLS). SNPs characteristics can be examined using the techniques that in turn, are helpful to resolve diverse parameters such as particle size, crystallinity, morphology, pores size, surface area, and purity and fractal dimensions.




Fig. 5. Plausible mechanism of green synthesis of SNPs by using *Allium sativum* extract [Reproduced from ref. 60].

UV-vis spectrophotometry

UV-vis spectroscopy mentions to absorption spectroscopy in the region of UV-vis spectrum. Light frequencies of the 200–800 nm are commonly used for portraying different metal NPs in the size range of 2 nm to 100 nms. UV-vis

spectroscopy is a crucial technique to ascertain the stability and formation of SNPs. UV-vis absorption measurement of the wavelength ranging from 250-400 nm is utilized to characterize SNPs (Fig. 6) [61, 65].




Fig. 6. UV-Vis absorption spectrum of biogenically synthesized SNPs [Reproduced from ref. 62].

XRD

XRD is a helpful tool for receiving information about the atomic and crystal structure of nanomaterials. XRD is a precious characterization technique to confirm the formation of SNPs, analyze the crystal structure, crystal planes and calculate the crystalline NPs size [70]. The standard JCPDS (Joint Committee on Powder Diffraction Standards) cards were used as a reference for confirmation of SNPs.

FT-IR

FT-IR is a molecular spectroscopy that analyses multifarious chemical functional groups in the regions between 400 and 4000 cm^{-1} . FT-IR tools are carried out to find out the possible biomolecules accountable for reduction, capping and efficacious stabilization of SNPs.

SEM

SEM is an essential analysis method that utilizes electrons instead of light to form a micro-image as an output. The SEM investigation is utilized to describe the shape, size, morphology and

distribution of biosynthesized SNPs (Fig. 7). The SEM microphotographs also evince the polydispersity and purity of resulting SNPs.

TEM

TEM is a valuable characterization technique and assists to examine the particle size of a material in nano-scale and to scrutiny the crystal structure carefully with high resolution. TEM assessments are proceeded in order to estimate the average NPs size and size distribution of the biosynthesized SNPs (Fig. 8).




Fig. 7. SEM images of synthesized SNPs [Reproduced from ref. 69].




Fig. 8. TEM images of synthesized SNPs [Reproduced from ref. 62].

EDS

EDS is an analytical method used for the chemical characterization or elemental analysis of SNPs. EDS provided the information about chemical composition, phase identification and purity of the biosynthesized SNPs.

AFM

The size, topography and surface area of the biosynthesized SNPs are examined using AFM. The advantage of AFM over ordinary microscopes such as TEM and SEM is that AFM technique makes three-dimensional (3D) images so that NPs volume and height and can be intended.

DLS

DLS method as a characteristic tool for particle size distribution (PSD) profiles of SNPs in solutions and/or colloidal suspensions has been broadly utilized in industry and scientific laboratory. DLS is characterized as a procedure by changing the dispersing light intensity fluctuation to procure the average diameter of SNPs. Real-time monitoring NPs size can be acknowledged by DLS because the assessment procedure of DLS is speedy and susceptible detection. Currently, DLS have been applied to identify cancer biomarkers and metal particles.

Apart from the aforesaid characterization tools, scientists also have utilized various precious characterization techniques for the affirmation of the NPs [71-76] (Fig. 9).

Applications of biogenically synthesized SNPs

SNPs have lots of stupendous applications for multifarious discipline of agriculture and biomedical. Nevertheless, the agricultural, biomedical and catalytic applications of the green synthesized SNPs are very prominent nowadays.




Fig. 9. Characterization techniques for NPs.

Accordingly, we have investigated in brief their eclectic and stupendous applications as guidance to new researchers for upcoming prospects (Table 2).

Salem *et al.* synthesized SNPs using *Alianthus altissima* leaves extract and reported to the seed germination study against tomato [58]. This study revealed that, the concentration dependent SNPs have the ability to enhance shoots and root growth of tomato. Khairan *et al.* synthesized spherical shaped SNPs using *Allium sativum* extract and studied the antifungal activity of as-prepared NPs. They carried out the antifungal activity of SNPs against *Candida albicans* [60].

Paralekar *et al.* reported the bio-inspired synthesis of spherical SNPs using *Azadirachta indica*, *Catharanthus roseus*, *Mangifera indica*, and *Polyalthia longifolia* leaves extract and reported their antibacterial activity using disk diffusion method. This antibacterial activity revealed that the synthesized SNPs showed better bactericidal efficacy against *Escherichia coli* and *Staphylococcus aureus* [61].

Najafi *et al.* reported the green synthesis of SNPs using *Cinnamomum zeylanicum* barks extracts and examined their effects on physiological and biochemical factors of *Lactuca sativa* [63].

Tripathi *et al.* synthesized random shaped SNPs using the leaf extract from *Ficus benghalensis* in the size of 2-15 nm and studied their catalytic detoxification of hexavalent chromium in water. They showed that the conversion rate of Cr(VI) into less toxic Cr(III) up to 88.7% in the presence of SNPs in 80 min. The optimal concentration ratios were maintained between SNPs and formic acid (10 ppm: 480 mM) [62].

Salem *et al.* described the green synthesis of SNPs using leaves extract from *Melia azedarach* were in the size of 5-80 nm and evaluated their seed germination activity against *Cucurbita pepo* [64]. Ragab *et al.* described the synthesis of spherical SNPs using *Oscimum basilicum* leaves

extracts and reported its effect on manganese stressed *Helianthus annuus* seedlings. They showed that the seed presoaking with medium doses of SNPs enhanced sunflower tolerance against Mn toxicity, balanced mineral uptake and photosynthetic pigments levels as well as maintaining of membrane stability [65].

Salem *et al.* reported the green synthesis of spherical shaped SNPs using *Punica granatum* peels extract and employed in agricultural application. This study evinced that the 200 ppm SNPs containing foliar spraying on tomato leaves are very advantageous to plant growth and generated healthy plant with high quality of tomato fruits and greener leaves compared with control [66].

Table 2. Applications of SNPs as-synthesized using various plants extracts

Sr. No.	Name of Plants	Applications	Ref.
1.	<i>Alianthus altissima</i>	Seed germination study	58
2.	<i>Allium sativum</i>	Antifungal activity	60
3.	<i>Azadirachta indica</i>	Antibacterial activity	61
4.	<i>Catharanthus roseus</i>	Antibacterial activity	61
5.	<i>Mangifera indica</i>	Antibacterial activity	61
6.	<i>Polyalthia longifolia</i>	Antibacterial activity	61
7.	<i>Ficus benghalensis</i>	Catalytic activity	62
8.	<i>Cinnamomum zeylanicum</i>	Agricultural application	63
9.	<i>Melia azedarach</i>	Seed germination study	64
10.	<i>Oscimum basilicum</i>	Seed germination study	65
11.	<i>Punica granatum</i>	Foliar spray	66
12.	<i>Rosmarinus officinalis</i>	Seed germination study	67
13.	<i>Rosmarinus officinalis</i>	Nematicidal activity	68

Moreover, a same author has described biosynthesis of SNPs using leaves extract of *Rosmarinus officinalis*. They also studied the seed germination activities of as-synthesized SNPs on *Cucumis sativus*. This study showed that the increased seed germination and seedling growth of *Cucumis sativus* significantly, when increase to concentration of synthesized SNPs [67].

Banna et al. synthesized spherical shaped SNPs using *Rosmarinus officinalis* leaves extracts and studied their nematocidal activity against *Meloidogyne javanica*. This nematocidal activity revealed that the SNPs synthesized using *Rosmarinus officinalis* leaves aqueous extracts could be used as nematocidal to manage *Meloidogyne javanica* infestation [68]

Conclusion

This review has presented the recent advancements in the discipline of green syntheses of SNPs by using plants. It also critically discusses precise mechanisms behind the green synthesis of SNPs. Plant broths may act as herbal reducing and/or stabilizing additives in the production of NPs. Syntheses of SNPs using

plant extract have several merits over the other known physical routes as it is sustainable, safer, affordable, non-noxious rapid synthesis and simplicity in protocols as well as simple to use. Plants have vast ability for the production of SNPs of wide range of stupendous applications for selective shapes and size. Further study needs to highlight the lucid mechanism behind the facile synthesis of SNPs, although few reports are existed in literature about this but just hypothesis. Therefore, further research needs to highlight the precise mechanism behind the fabrication of SNPs and improve their applications in diverse sectors.

Acknowledgement

The author SG is grateful to Dr. R. S. Oza and Dr. S. S. Pansambal for their constant valuable guidance.

Conflict of interest

The authors declare that there are no conflicts of interest regarding the publication of this manuscript.

References

1. M.B. Gawande, A. Goswami, F.X. Felpin, T. Asefa, X. Huang, R. Silva, X. Zou, R. Zboril, R.S. Varma, Cu and Cu-based nanoparticles: synthesis and applications in catalysis. *Chem. Rev.* 116 (2016) 3722-3811.
2. S. Matussin, M.H. Harunsani, A.L. Tan, M.M. Khan, Plant-Extract-Mediated SnO₂ Nanoparticles: Synthesis and Applications. *ACS Sustainable Chemistry & Engineering*. 8 (2020) 3040-3054.
3. N. Tarannum, Y.K. Gautam, Facile green synthesis and applications of silver nanoparticles: a state-of-the-art review. *RSC Advances*. 9 (2019) 34926-34948.
4. R. Ghosh Chaudhuri, S. Paria, Core/shell nanoparticles: classes, properties, synthesis mechanisms, characterization, and applications. *Chem. Rev.* 112(2012) 2373-2433.
5. S. Ghotekar, A review on plant extract mediated biogenic synthesis of CdO nanoparticles and their recent applications. *Asian Journal of Green Chemistry*. 3 (2019) 187-200.
6. T. Pagar, S. Ghotekar, K. Pagar, S. Pansambal, R. Oza, A review on bio-synthesized Co₃O₄ nanoparticles using plant extracts and their diverse applications. *Journal of Chemical Reviews*. 1 (2019) 260-270.
7. A. Nikam, T. Pagar, S. Ghotekar, K. Pagar, S. Pansambal, A review on plant extract mediated green synthesis of zirconia nanoparticles and their miscellaneous

- applications. *Journal of Chemical Reviews*. 1 (2019) 154-163.
8. S. Ghotekar, Plant extract mediated biosynthesis of Al_2O_3 nanoparticles-a review on plant parts involved, characterization and applications. *Nanochemistry Research*. 4 (2019) 163-169.
9. G. Oza, A. Reyes-Calderón, A. Mewada, L.G. Arriaga, G.B. Cabrera, D.E. Luna, H.M. Iqbal, M. Sharon, A. Sharma, Plant-based metal and metal alloy nanoparticle synthesis: a comprehensive mechanistic approach. *Journal of Materials Science*. (2020) 1-22.
10. S. Ghotekar, S. Pansambal, S.P. Pawar, T. Pagar, R. Oza, S. Bangale, Biological activities of biogenically synthesized fluorescent silver nanoparticles using *Acanthospermum hispidum* leaves extract. *SN Applied Sciences*. 1 (2019) 1342.
11. P. Korde, S. Ghotekar, T. Pagar, S. Pansambal, R. Oza, D. Mane, Plant Extract Assisted Eco-benevolent Synthesis of Selenium Nanoparticles-A Review on Plant Parts Involved, Characterization and Their Recent Applications. *Journal of Chemical Reviews*. 2 (2020) 157-168.
12. Y.B. Aher, G.H. Jain, G.E. Patil, A.R. Savale, S.K. Ghotekar, D.M. Pore, S.S. Pansambal, K.K. Deshmukh, Biosynthesis of copper oxide nanoparticles using leaves extract of *Leucaena leucocephala* L. and their promising upshot against diverse pathogens. *International Journal of Molecular and Clinical Microbiology*. 7 (2017) 776-786.
13. K. Pagar, S. Ghotekar, T. Pagar, A. Nikam, S. Pansambal, R. Oza, D. Sanap, H. Dabhane, Antifungal activity of biosynthesized CuO nanoparticles using leaves extract of *Moringa oleifera* and their structural characterizations. *Asian Journal of Nanosciences and Materials*. 3 (2020) 15-23.
14. D.R. Kamble, S.V. Bangale, S.K. Ghotekar, S.R. Bamane, Efficient synthesis of CeVO_4 nanoparticles using combustion route and their antibacterial activity. *Journal of Nanostructures*. 8 (2018) 144-151.
15. N.M. Ishak, S.K. Kamarudin, S.N. Timmiati, Green synthesis of metal and metal oxide nanoparticles via plant extracts: an overview. *Materials Research Express*. 6 (2019) 112004.
16. L. Syedmoradi, M. Daneshpour, M. Alvandipour, F.A. Gomez, H. Hajghassem, K. Omidfar, Point of care testing: The impact of nanotechnology. *Biosensors and Bioelectronics*. 87 (2017) 373-387.
17. S. Ghotekar, S. Pansambal, K. Pagar, O. Pardeshi, R. Oza, Synthesis of CeVO_4 nanoparticles using sol-gel auto combustion method and their antifungal activity. *Nanochemistry Research*. 3 (2018) 189-196.
18. A. Savale, S. Ghotekar, S. Pansambal, O. Pardeshi, Green synthesis of fluorescent CdO nanoparticles using *Leucaena leucocephala* L. extract and their biological activities. *J Bacteriol Mycol Open Access*. 5 (2017) 00148.
19. S.H. Gebre, M.G. Sendeku, New frontiers in the biosynthesis of metal oxide nanoparticles and their environmental applications: an overview. *SN Applied Sciences*. 1 (2019) 928.
20. S. Ghotekar, A. Savale, S. Pansambal, Phytofabrication of fluorescent silver nanoparticles from *Leucaena leucocephala* L. leaves and their biological activities. *Journal of Water and Environmental Nanotechnology*. 3 (2018) 95-105.
21. T. Pagar, S. Ghotekar, S. Pansambal, R. Oza, B.P. Marasini, Facile Plant Extract Mediated Eco-Benevolent Synthesis and

- Recent Applications of CaO-NPs: A State-of-the-art Review. *Journal of Chemical Reviews*. 2 (2020) 201-210.
22. S.K. Ghotekar, P.S. Vaidya, S.N. Pande, S.P. Pawar, Synthesis of silver nanoparticles by using 3-methyl pyrazol 5-one (chemical reduction method) and its characterizations. *Int. J. Multidis. Res and Deve.* 2 (2015) 419-422.
23. S.K. Ghotekar, S.N. Pande, S.S. Pansambal, D.S. Sanap, K.M. Mahale, B. Sonawane, Biosynthesis of silver nanoparticles using unripe fruit extract of *Annona reticulata* L. and its characterization. *World J. Pharm. and Pharm. Sci.* 4 (2015) 1304-1312.
24. V. Hoseinpour, N. Ghaemi, Green synthesis of manganese nanoparticles: Applications and future perspective–A review. *Journal of Photochemistry and Photobiology B: Biology.* 189 (2018) 234-243.
25. S. Pansambal, K. Deshmukh, A. Savale, S. Ghotekar, O. Pardeshi, G. Jain, Y. Aher, D. Pore, Phytosynthesis and biological activities of fluorescent CuO nanoparticles using *Acanthospermum hispidum* L. extract. *Journal of Nanostructures.* 7 (2017) 165-174.
26. S. Pansambal, S. Ghotekar, S. Shewale, K. Deshmukh, N. Barde, P. Bardapurkar, Efficient synthesis of magnetically separable $\text{CoFe}_2\text{O}_4/\text{SiO}_2$ nanoparticles and its potent catalytic applications for the synthesis of 5-aryl-1, 2, 4-triazolidine-3-thione derivatives. *Journal of Water and Environmental Nanotechnology.* 4 (2019) 174-186.
27. S. Bangale, S. Ghotekar, Bio-fabrication of Silver nanoparticles using *Rosa Chinensis* L. extract for antibacterial activities. *International Journal of Nano Dimension.* 10 (2019) 217-224.
28. S. Rajeshkumar, P. Naik, Synthesis and biomedical applications of cerium oxide nanoparticles–a review. *Biotechnology Reports.* 17 (2018) 1-5.
29. S. Pansambal, S. Gavande, S. Ghotekar, R. Oza, K. Deshmukh, Green Synthesis of CuO Nanoparticles using *Ziziphus Mauritiana* L. Extract and Its Characterizations. *Int. J. Sci. Res. in Sci. and Tech.* 3 (2017) 1388-1392.
30. S. Pansambal, S. Ghotekar, R. Oza, K. Deshmukh, Biosynthesis of CuO nanoparticles using aqueous extract of *Ziziphus mauritiana* L. leaves and their Catalytic performance for the 5-aryl-1, 2, 4-triazolidine-3-thione derivatives synthesis. *Int. J. Sci. Res. Sci. Technol.* 5 (2019) 122-128.
31. E.A. Ilardi, E. Vitaku, J.T. Njardarson, Data-mining for sulfur and fluorine: An evaluation of pharmaceuticals to reveal opportunities for drug design and discovery: Mini perspective. *Journal of Medicinal Chemistry.* 57 (2014) 2832-2842.
32. C.M. Griffith, J.E. Woodrow, J.N. Seiber, Environmental behavior and analysis of agricultural sulfur. *Pest management science.* 71 (2015) 1486-1496.
33. B.B. Sadykov, N.N. Volynskova, S.S. Namazov, B.M. Beglov, Technology for manufacturing fertilizer “Superfos” containing nitrogen, phosphorus, sulfur and calcium. *Russian Journal of Applied Chemistry.* 81 (2008) 1667-1672.
34. G. Li, J. Sun, W. Hou, S. Jiang, Y. Huang, J. Geng, Three-dimensional porous carbon composites containing high sulfur nanoparticle content for high-performance lithium–sulfur batteries. *Nature communications.* 7 (2016) 1-0.
35. K.J. Rao, S. Paria, Use of sulfur nanoparticles as a green pesticide on *Fusarium solani* and *Venturia inaequalis*

- phytopathogens. *RSC advances*. 3 (2013) 10471-10478.
36. S.R. Choudhury, K.K. Nair KK, R. Kumar, R. Gogoi, C. Srivastava, M. Gopal, B.S. Subhramanyam, C. Devakumar, A. Goswami, Nanosulfur: a potent fungicide against food pathogen, *Aspergillus niger*. *AIP Conference Proceedings*. 1276 (2010) 154-157.
37. R. Ahmadi, M.K. Amini, J.C. Bennett, Pt-Co alloy nanoparticles synthesized on sulfur-modified carbon nanotubes as electrocatalysts for methanol electrooxidation reaction. *Journal of catalysis*. 292 (2012) 81-89.
38. P. Santiago, E. Carvajal, D. Mendoza, L. Rendon, Synthesis and structural characterization of sulfur nanowires. *Microscopy and Microanalysis*. 12 (2006) 690-691.
39. Y. Lan, B. Deng, C. Kim, E.C. Thornton, H. Xu, Catalysis of elemental sulfur nanoparticles on chromium (VI) reduction by sulfide under anaerobic conditions. *Environmental science & technology*. 39 (2005) 2087-2094.
40. I. Porras, Sulfur-33 nanoparticles: a Monte Carlo study of their potential as neutron capturers for enhancing boron neutron capture therapy of cancer. *Applied Radiation and Isotopes*. 69 (2011) 1838-1841.
41. S. Roy Choudhury, S. Roy, A. Goswami, S. Basu, Polyethylene glycol-stabilized sulphur nanoparticles: an effective antimicrobial agent against multidrug-resistant bacteria. *Journal of antimicrobial chemotherapy*. 67 (2012) 1134-1137.
42. S. Shankar, R. Pangeni, J.W. Park, J.W. Rhim, Preparation of sulfur nanoparticles and their antibacterial activity and cytotoxic effect. *Materials Science and Engineering: C*. 92 (2018) 508-517.
43. F. Zahran, M. Hammadi, M. Al-dulaimi, M. Sebaiy, Potential Role of Sulfur Nanoparticles as Antitumor and Antioxidant in Mice. *Der Pharmacia Lettre*. 10 (2018) 7-26.
44. L. Jaiswal, S. Shankar, J.W. Rhim, Carrageenan-based functional hydrogel film reinforced with sulfur nanoparticles and grapefruit seed extract for wound healing application. *Carbohydrate polymers*. 224 (2019) 115191.
45. A.S. Deshpande, R.B. Khomane, B.K. Vaidya, R.M. Joshi, A.S. Harle, B.D. Kulkarni, Sulfur nanoparticles synthesis and characterization from H₂S gas, using novel biodegradable iron chelates in W/O microemulsion. *Nanoscale Research Letters*. 3 (2008) 221.
46. R.G. Chaudhuri, S. Paria, Synthesis of sulfur nanoparticles in aqueous surfactant solutions. *Journal of colloid and interface science*. 343 (2010) 439-446.
47. W. Wang, Y.C. Lu, H. Huang, A.J. Wang, J.R. Chen, J.J. Feng, Solvent-free synthesis of sulfur-and nitrogen-co-doped fluorescent carbon nanoparticles from glutathione for highly selective and sensitive detection of mercury (II) ions. *Sensors and Actuators B: Chemical*. 202 (2014) 741-747.
48. M. Suleiman, M. Al-Masri, A. Al Ali, D. Aref, A. Hussein, I. Saadeddin, I. Warad, Synthesis of nano-sized sulfur nanoparticles and their antibacterial activities. *Journal of Materials and Environmental Science*. 6 (2015) 513-518.
49. M. Shamsipur, S.M. Pourmortazavi, M. Roushani, I. Kohsari, S.S. Hajimirsadeghi, Novel approach for electrochemical preparation of sulfur nanoparticles. *Microchimica Acta*. 173 (2011) 445-451.
50. X.Z. Cheng, K. Cheng, J. Liu, X.F. Sun, Synthesis and characterizations of nanoparticle sulfur using eggshell

- membrane as template. *Materials Science Forum*. 675 (2011) 279-282.
51. Y. Guo, Y. Deng, J. Zhao, Z. Wang, H. Zhang, Synthesis and characterization of sulfur nanoparticles by liquid phase precipitation method. *Acta Chim Sinica*. 63 (2005) 337-340.
 52. B. Meenatchi, V. Renuga, Protic ionic liquids assisted synthesis and characterization of sulfur nanoparticles and CdS and ZnS nanomaterials. *Chemical Science Transactions*. (2015) 577-587.
 53. X.Y. Xie, L.Y. Li, P.S. Zheng, W.J. Zheng, Y. Bai, T.F. Cheng, J. Liu, Facile synthesis, spectral properties and formation mechanism of sulfur nanorods in PEG-200. *Materials Research Bulletin*. 47 (2012) 3665-3669.
 54. X.Y. Xie, W.J. Zheng, Y. Bai, J. Liu, Cystine modified nano-sulfur and its spectral properties. *Materials letters*. 63 (2009) 1374-1376.
 55. L. Chen, L. Guo, Z. Li, H. Zhang, J. Lin, J. Huang, S. Jin, X. Chen, Towards intrinsic magnetism of graphene sheets with irregular zigzag edges. *Scientific reports*. 3 (2013) 1-6.
 56. E. Bura-Nakić, M. Marguš, D. Jurašin, I. Milanović, I. Ciglenečki-Jušić, Chronoamperometric study of elemental sulphur (S) nanoparticles (NPs) in NaCl water solution: new methodology for S NPs sizing and detection. *Geochemical transactions*. 16 (2015) 1-9.
 57. V.J. Kouzegaran, K. Farhadi, Green synthesis of Sulphur Nanoparticles assisted by a herbal surfactant in aqueous solutions. *Micro & Nano Letters*. 12 (2017) 329-334.
 58. N.M. Salem, L.S. Albanna, A.O. Abdeen, Q.I. Ibrahim, A.M. Awwad, Sulfur nanoparticles improves root and shoot growth of tomato. *J. Agric. Sci*. 8 (2016) 179.
 59. A.M. Awwad, N.M. Salem, A.O. Abdeen, Novel approach for synthesis sulfur (S-NPs) nanoparticles using Albizia julibrissin fruits extract. *Adv. Mat. Lett*. 6 (2015) 432-435.
 60. K. Khairan, Zahraturreiaz, Z. Jalil, Green synthesis of sulphur nanoparticles using aqueous garlic extract (*Allium sativum*). *Rasayan J. Chem.*, 12 (2019) 50-57.
 61. P. Paralikar, M. Rai, Bio-inspired synthesis of sulphur nanoparticles using leaf extract of four medicinal plants with special reference to their antibacterial activity. *IET Nanobiotechnology*. 12 (2017) 25-31.
 62. S. Najafi, S.M. Razavi, M. Khoshkam, A. Asadi, Effects of green synthesis of sulfur nanoparticles from Cinnamomum zeylanicum barks on physiological and biochemical factors of Lettuce (*Lactuca sativa*). *Physiology and Molecular Biology of Plants*. (2020) 1-2.
 63. R.M. Tripathi, R.P. Rao, T. Tsuzuki, Green synthesis of sulfur nanoparticles and evaluation of their catalytic detoxification of hexavalent chromium in water. *RSC advances*. 8 (2018) 36345-36352.
 64. N.M. Salem, L.S. Albanna, A.M. Awwad, Q.M. Ibrahim, A.O. Abdeen, Green synthesis of nano-sized sulfur and its effect on plant growth. *J. Agric. Sci*. 8 (2016) 5539.
 65. G.A. Ragab, K.M. Saad-Allah, Green synthesis of sulfur nanoparticles using Ocimum basilicum leaves and its prospective effect on manganese-stressed Helianthus annuus (L.) seedlings. *Ecotoxicology and Environmental Safety*. 191 (2020) 110242.
 66. N.M. Salem, L.S. Albanna, A.M. Awwad, Green synthesis of sulfur nanoparticles using Punica granatum peels and the effects on the growth of tomato by foliar

- spray applications. *Environmental Nanotechnology, Monitoring & Management*. 6 (2016) 83-87.
67. L.S. Albanna, N.M. Salem, A.M. Awwad, Seed germination and growth of cucumber (*Cucumis sativus*): effect of nano-crystalline sulfur. *The Journal of Agricultural Science*. 8 (2016) 219-225.
 68. L.S. Al Banna, N.M. Salem, G.A. Jaleel, A.M. Awwad, Green synthesis of sulfur nanoparticles using *Rosmarinus officinalis* leaves extract and nematicidal activity against *Meloidogyne javanica*. *Chemistry International*. 6 (2020) 137-143.
 69. A.M. Awwad, A.O. Abdeen, Phytochemical and Spectral Studies of Synthesis sulfur Nanoparticles using *Sophora japonica* Pods Extract. *Journal of Advances in Chemistry*. 11 (2015) 3426-3432.
 70. U. Holzwarth, N. Gibson, The Scherrer equation versus the 'Debye-Scherrer equation'. *Nature nanotechnology*. 6 (2011) 534.
 71. S. Ghotekar, H. Dabhane, S. Pansambal, R. Oza, P. Tambade, V. Medhane, A Review on Biomimetic Synthesis of Ag_2O Nanoparticles using Plant Extract, Characterization and its Recent Applications, *Ad. J. Chem. B*, 2 (2020) 102-111.
 72. Y. Orooji, M. Ghanbari, O. Amiri, M. Salavati-Niasari, Facile fabrication of silver iodide/graphitic carbon nitride nanocomposites by notable photo-catalytic performance through sunlight and antimicrobial activity. *Journal of Hazardous Materials*. 389 (2020) 122079.
 73. M. Ghanbari, M. Salavati-Niasari, Ti_4CdI_6 nanostructures: facile sonochemical synthesis and photocatalytic activity for removal of organic dyes. *Inorganic chemistry*. 57 (2018) 11443-11455.
 74. S. Gholamrezaei, M. Ghanbari, O. Amiri, M. Salavati-Niasari, L.K. Foong, BaMnO_3 nanostructures: Simple ultrasonic fabrication and novel catalytic agent toward oxygen evolution of water splitting reaction. *Ultrasonics sonochemistry*. 61 (2020) 104829.
 75. M. Ghanbari, M. Bazarganipour, M. Salavati-Niasari, Photodegradation and removal of organic dyes using CuI nanostructures, green synthesis and characterization. *Separation and Purification Technology*. 173 (2017) 27-36.
 76. M. Ghanbari, F. Soofivand, M. Salavati-Niasari, Simple synthesis and characterization of $\text{Ag}_2\text{CdI}_4/\text{AgI}$ nanocomposite as an effective photocatalyst by co-precipitation method. *Journal of Molecular Liquids*. 223 (2016) 21-28.

HOW TO CITE THIS ARTICLE

Ghotekar, S., Pagar, T., Pansambal, S., Oza, R., A Review on Green Synthesis of Sulfur Nanoparticles via Plant Extract, Characterization and its Applications, *Ad. J. Chem. B*, 2 (2020) 128-143.

DOI: 10.22034/ajcb.2020.109501

URL: http://www.ajchem-b.com/article_109501.html

